

Ascend Performance Materials Vydyn® 65A Nylon 66, General Purpose, intermediate viscosity, DAM

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Vydyn® 65A is a medium-viscosity, heat-stabilized PA66 resin suitable for injection-molding extrusion and compounding applications. It is available in natural color only. Vydyn 65A resin offers high strength, rigidity and toughness over a broad range of demanding applications and good fluid resistance to a wide variety of chemicals, solvents and oils. Typical Applications/End Uses: Typical uses include packaging films, monofilaments, bristles, rods, tubing, sheet and extruded profiles. Availability: Asia Pacific Europe North America Additive: Heat Stabilizer Slip Features: General Purpose Good Chemical Resistance Good Toughness Heat Stabilized High Rigidity High Strength Medium Viscosity Oil Resistant Solvent Resistant Uses: Industrial Applications Monofilaments Profiles Rods Sheet Tubing Appearance: Natural Color Forms: Pellets Processing Method: Extrusion and Injection Molding Information provided by Ascend

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ascend-Performance-Materials-Vydyn-65A-Nylon-66-General-Purpose-intermediate-viscosity-DAM.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ISO 1183
Water Absorption	8.5 %	8.5 %	24 hrs; ISO 62
Moisture Absorption at Equilibrium	2.5 %	2.5 %	Equilibrium at 50%rh; ISO 62
Linear Mold Shrinkage	0.020 cm/cm @Thickness 2.00 mm	0.020 in/in @Thickness 0.0787 in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.018 cm/cm @Thickness 2.00 mm	0.018 in/in @Thickness 0.0787 in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	ISO 527-2
Tensile Strength, Yield	85.0 MPa	12300 psi	ISO 527-2
Elongation at Break	>= 25 %	>= 25 %	ISO 527-2
Elongation at Yield	5.5 %	5.5 %	ISO 527-2
Tensile Modulus	3.10 GPa	450 ksi	ISO 527-2
Flexural Strength	75.0 MPa	10900 psi	ISO 178
Flexural Modulus	2.80 GPa	406 ksi	ISO 178
Poissons Ratio	0.40	0.40	ISO 527-2

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched (ISO)	6.00 kJ/m²	2.86 ft-lb/in²	ISO 180
	6.00 kJ/m²	2.86 ft-lb/in²	ISO 180
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.600 J/cm²	2.86 ft-lb/in²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	0.600 J/cm²	2.86 ft-lb/in²	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	10.0 µm/m-°C	5.56 µin/in-°F	ISO 11359-2
	@Thickness 2.00 mm, Temperature 23.0 - 55.0 °C	@Thickness 0.0787 in, Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	10.0 µm/m-°C	5.56 µin/in-°F	ISO 11359-2
	@Thickness 2.00 mm, Temperature 23.0 - 55.0 °C	@Thickness 0.0787 in, Temperature 73.4 - 131 °F	
Melting Point	260 °C	500 °F	ISO 11357-3
Deflection Temperature at 0.46 MPa (66 psi)	200 °C	392 °F	ISO 75-2/B
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ISO 75-2/A

Processing Properties	Metric	English	Comments
Zone 1	250 - 295 °C	482 - 563 °F	
Zone 2	250 - 295 °C	482 - 563 °F	
Zone 3	250 - 295 °C	482 - 563 °F	
Zone 4	250 - 295 °C	482 - 563 °F	
Zone 5	250 - 295 °C	482 - 563 °F	
Die Temperature	270 - 295 °C	518 - 563 °F	

Processing Properties	Metric	English	Comments
Back Pressure	3.00 - 17.0 MPa	435 - 2470 psi	

Descriptive Properties	Value	Comments
Blown Film Bath Temperature	20-80°C	
Chill Roll Temperature (Cast Film)	20-80°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China