

Ashley Polymers Ashlene® 833 Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Basic Nylon 6 medium viscosity, with high residual monomer. Highly flexible and high strength, particularly suited for monofilament extrusion. Data provided by the manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-833-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ASTM D792
Water Absorption	1.9 %	1.9 %	24 hrs; ASTM D570
Water Absorption at Saturation	9.6 %	9.6 %	ASTM D570
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	79.0 MPa	11500 psi	ASTM D638
Elongation at Break	300 %	300 %	ASTM D638
Flexural Strength	62.0 MPa	8990 psi	ASTM D790
Flexural Modulus	1.50 GPa	218 ksi	ASTM D790
Izod Impact, Notched	1.87 J/cm	3.50 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	222 °C	432 °F	ASTM D3418

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China