

Axiall 15644 Wire & Cable Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Semi-rigid insulation compound recommended for Style #1061 applications. Maximum service temperature of 105°C. Information provided by Georgia Gulf. Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-15644-Wire-Cable-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 - 1.37 g/cc	1.33 - 1.37 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	58 - 64	58 - 64	delayed; ASTM D-2240
Tensile Strength, Yield	22.3 MPa	3230 psi	ASTM D-638
Elongation at Yield	300 %	300 %	ASTM D-638
100% Modulus	0.0200 GPa	2.90 ksi	ASTM D-638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-5.00 °C	23.0 °F	ASTM D-746
Oxygen Index	28.3 %	28.3 %	ASTM D-638

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	50% RH; ASTM D-257

Processing Properties	Metric	English	Comments
Melt Temperature	188 °C	370 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China