

Azoty Tarnow™ TARNOFORM 411 POM

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Easy flowing, internally strengthened grade for injection molding of thin walled parts of very high mechanical requirements. Information provided by Zakłady Azotowe w Tarnowie-Moscicach S.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Azoty-Tarnow-TARNOFORM-411-POM.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.036 cm/cm	0.036 in/in	60x60x4
Linear Mold Shrinkage, Transverse	0.0335 cm/cm	0.0335 in/in	ISO 294-4
Melt Flow	13 g/10 min @Load 2.16 kg, Temperature 190 °C	13 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ISO 2039-2
Ball Indentation Hardness	155 MPa	22500 psi	358 N; ISO 2039-1
Tensile Strength, Yield	68.0 MPa	9860 psi	ISO 527
Elongation at Break	30 %	30 %	ISO 527
Flexural Strength	68.0 MPa	9860 psi	ISO 178
Izod Impact, Notched (ISO)	6.00 kJ/m ²	2.86 ft-lb/in ²	1A; ISO 180
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	1eA; ISO 179

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.48 J/g-°C	0.354 BTU/lb-°F	
Melting Point	170 °C	338 °F	10°C/min.; ISO 3146
Maximum Service Temperature, Air	100 °C	212 °F	
Deflection Temperature at 1.8 MPa (264 psi)	115 °C	239 °F	ISO 75
Vicat Softening Point	161 °C	322 °F	50 N; ISO 306
	HB	HB	

Flammability: UL 94 Thermal Properties	Metric @ Thickness 3.20 mm	English @ Thickness 0.126 in	Comments
---	-------------------------------	---------------------------------	----------

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093
Dielectric Constant	3.9	3.9	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	25.0 kV/mm	635 kV/in	IEC 60243
Dissipation Factor	0.0085	0.0085	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	1.9 sec	1.9 sec	
Comparative Tracking Index	600 V	600 V	IEC 112

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 230 °C	356 - 446 °F	Barrel temperature
Mold Temperature	60.0 - 120 °C	140 - 248 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China