

BASF Elastollan C 88 A TPUR

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Description: Thermoplastic Polyester Polyurethane Elastomers with excellent mechanical properties and chemical resistance, outstanding wear resistance, high tear and tensile strength, good damping characteristics and a high resilience performance. Typical Applications: Spiral tubing, pneumatic tubing, round and v-beltting, technical moldings, e.g. bushes, dust caps, seals, blow molding bellows, and mining screens. Note: Quoted results are from measurements on injection molded test platens, post tempered for 20 hours at 100°C. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Elastollan-C-88-A-TPUR.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183-1-A

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	88	88	ISO 868
Hardness, Shore D	37	37	ISO 686
Tensile Strength	38.0 MPa	5510 psi	after storage in water at 80°C for 42 days; ISO 37
	50.0 MPa	7250 psi	ISO 37
	3.50 MPa	508 psi	ISO 37
	@Strain 20.0 %	@Strain 20.0 %	
	6.00 MPa	870 psi	ISO 37
	@Strain 100 %	@Strain 100 %	
	13.0 MPa	1890 psi	ISO 37
	@Strain 300 %	@Strain 300 %	
Elongation at Break	600 %	600 %	ISO 37
	650 %	650 %	after storage in water at 80°C for 42 days; ISO 37
Charpy Impact, Notched	NB	NB	DIN EN ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	DIN EN ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tear Strength	75.0 kN/m	428 pli	DIN ISO 34-1/Bb

Mechanical Properties	Metric	English	Comments
Compression Set	25 %	25 %	ISO 815
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	40 %	40 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	160 - 220 °C	320 - 428 °F	Extrusion
Mold Temperature	20.0 - 70.0 °C	68.0 - 158 °F	

Descriptive Properties	Value	Comments
Commercial Status	North America	
Primary Processing Technique	Extrusion	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China