

## BASF Lucalen® A 2910 M Q 47 Ethylene/Acrylate Copolymer

Category : Polymer , Thermoplastic , Ethylene Acrylic Acid

### Material Notes:

Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Lucalen-A-2910-M-Q-47-EthyleneAcrylate-Copolymer.php](http://www.lookpolymers.com/polymer_BASF-Lucalen-A-2910-M-Q-47-EthyleneAcrylate-Copolymer.php)

| Physical Properties | Metric     | English       | Comments |
|---------------------|------------|---------------|----------|
| Density             | 0.927 g/cc | 0.0335 lb/in³ |          |

| Mechanical Properties   | Metric     | English  | Comments |
|-------------------------|------------|----------|----------|
| Tensile Strength, Yield | 6.00 MPa   | 870 psi  |          |
| Elongation at Break     | >= 50 %    | >= 50 %  |          |
| Tensile Modulus         | 0.0840 GPa | 12.2 ksi |          |

| Thermal Properties | Metric  | English | Comments |
|--------------------|---------|---------|----------|
| Melting Point      | 96.0 °C | 205 °F  |          |

| Electrical Properties  | Metric             | English            | Comments |
|------------------------|--------------------|--------------------|----------|
| Electrical Resistivity | >= 1.00e+15 ohm-cm | >= 1.00e+15 ohm-cm |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China