

BASF Lucalen® A 3110 M Q 244 Ethylene/Acrylate Copolymer

Category : Polymer , Thermoplastic , Ethylene Acrylic Acid

Material Notes:

Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lucalen-A-3110-M-Q-244-EthyleneAcrylate-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.928 g/cc	0.0335 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	5.00 MPa	725 psi	
Elongation at Break	>= 50 %	>= 50 %	
Tensile Modulus	0.0740 GPa	10.7 ksi	

Thermal Properties	Metric	English	Comments
Melting Point	99.0 °C	210 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China