

BASF Lupranate® 5020 Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® 5020 Isocyanate is a low free-NCO prepolymer based on pure MDI. The 9.5% free-NCO of Lupranate® 5020 Isocyanate lends itself to one-component applications, such as but not limited to, moisture cure sealants, binders and coatings. In addition, the low free-NCO of this prepolymer helps reduce shrinkage in cast elastomers and one-shot systems. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-5020-Isocyanate.php

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in ³	
Viscosity	2500 cP	2500 cP	
Vapor Pressure	<= 1.33e-8 bar @Temperature 25.0 °C	<= 0.00000998 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	200 °C	392 °F	

Descriptive Properties	Value	Comments
Color	Yellow	
Composition	NCO content	0.095

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China