

BASF Lupranate® MI Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® MI Isocyanate is pure diphenylmethane diisocyanate containing a higher amount of 2,4' isomer than Lupranate M Isocyanate or Lupranate MS Isocyanate. Lupranate MI Isocyanate has a functionality of 2.0 and is liquid at room temperature. Lupranate MI isocyanate is used in the isocyanate component for the preparation of flexible, semi-flexible and microcellular urethane foams. Lupranate MI Isocyanate can also be used for the production of adhesives, coatings and sealants. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-MI-Isocyanate.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in³	
Vapor Pressure	4.00e-7 bar @Temperature 25.0 °C	0.000300 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	10.0 - 15.0 °C	50.0 - 59.0 °F	Freezing Point
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	199 °C	390 °F	

Descriptive Properties	Value	Comments
Color	Colorless to Reddish Yellow	
Composition	2,4' Isomer	0.5
	Hydrolyzable Chlorine	<400 ppm
	NCO content	0.335
Purity	0.995	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China