

## BASF Lupranate® R2500 Isocyanate

Category : Fluid

**Material Notes:**

Description: Lupranate® R2500 Isocyanate is a polymeric MDI with a functionality of approximately 2.7. Careful control of the MDI distribution in Lupranate R2500 Isocyanate helps provide uniform reactivity. This isocyanate can be used for the production of rigid insulation foams by molding, spraying, and frothing. It is also used for rigid and semi-flexible integral skin foams. CASE applications include floor coatings and microcellular elastomers. Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Lupranate-R2500-Isocyanate.php](http://www.lookpolymers.com/polymer_BASF-Lupranate-R2500-Isocyanate.php)

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in <sup>3</sup>	
Viscosity	190 cP	190 cP	
Vapor Pressure	2.67e-7 bar @Temperature 25.0 °C	0.000200 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	200 °C	392 °F	

Descriptive Properties	Value	Comments
Color	Dark Brown	
Composition	Hydrolyzable Chlorine	0.00035
	NCO content	0.315

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China