

BASF Novolen® 2900 H Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Injection molded and thermoformed parts. Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Novolen-2900-H-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in ³	
Water Absorption	0.10 %	0.10 %	
Moisture Absorption at Equilibrium	0.10 %	0.10 %	
Linear Mold Shrinkage, Flow	0.013 cm/cm	0.013 in/in	
Melt Flow	3.0 g/10 min @Load 2.16 kg, Temperature 230 °C	3.0 g/10 min @Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	14.0 MPa	2030 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	4.0 %	4.0 %	
Tensile Modulus	0.650 GPa	94.3 ksi	
Charpy Impact Unnotched	NB	NB	
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	
Charpy Impact, Notched	9.50 J/cm ²	45.2 ft-lb/in ²	
	1.70 J/cm ² @Temperature -30.0 °C	8.09 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	150 µm/m-°C @Temperature 20.0 °C	83.3 µin/in-°F @Temperature 68.0 °F	
Melting Point	163 °C	325 °F	

Thermal Properties (on psi)	Metric 62.0 °C	English 144 °F	Comments
Deflection Temperature at 0.46 MPa (264 psi)	46.0 °C	115 °F	
Vicat Softening Point	38.0 °C	100 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Constant	2.3	2.3	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	140 kV/mm	3560 kV/in	
Dissipation Factor	0.000070	0.000070	
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.00020	0.00020	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China