

## BASF Pluracol® 1528 FF Molded Foam Polyol

Category : Fluid

### Material Notes:

Description: Pluracol® 1528FF polyol is a graft polyol based on a high reactivity polyether triol containing approximately 45% acrylonitrile/styrene copolymer. Pluracol 1528FF is a "fine-filtered" version of Pluracol 1528 polyol that is designed for more stringent filters in certain graft polyol operations. Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Pluracol-1528-FF-Molded-Foam-Polyol.php](http://www.lookpolymers.com/polymer_BASF-Pluracol-1528-FF-Molded-Foam-Polyol.php)

| Physical Properties | Metric               | English              | Comments |
|---------------------|----------------------|----------------------|----------|
| Density             | 1.00 g/cc            | 0.0361 lb/in³        |          |
|                     | @Temperature 55.0 °C | @Temperature 131 °F  |          |
|                     | 1.01 g/cc            | 0.0365 lb/in³        |          |
|                     | @Temperature 40.0 °C | @Temperature 104 °F  |          |
|                     | 1.02 g/cc            | 0.0368 lb/in³        |          |
|                     | @Temperature 25.0 °C | @Temperature 77.0 °F |          |
| Viscosity           | 1743 cP              | 1743 cP              |          |
|                     | @Temperature 55.0 °C | @Temperature 131 °F  |          |
|                     | 3020 cP              | 3020 cP              |          |
|                     | @Temperature 40.0 °C | @Temperature 104 °F  |          |
|                     | 5768 cP              | 5768 cP              |          |
|                     | @Temperature 25.0 °C | @Temperature 77.0 °F |          |

| Processing Properties | Metric     | English    | Comments |
|-----------------------|------------|------------|----------|
| Moisture Content      | <= 0.050 % | <= 0.050 % | STI 3062 |

| Descriptive Properties | Value                | Comments      |
|------------------------|----------------------|---------------|
| Color                  | Cream Opaque Liquid  |               |
| Hydroxyl Number        | 17.0 - 21.0 mg KOH/g | STI 3007/3162 |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China