

BASF Ultramid® B3GM35 BK 30564 15/25% Glass/Mineral Filled PA6 (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass/Mineral Reinforced

Material Notes:

Description: 25% mineral-filled and 15% glass-fiber reinforced injection-molding grade for industrial articles having medium rigidity and high dimensional stability, used e.g. for covers and handles. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultramid-B3GM35-BK-30564-1525-GlassMineral-Filled-PA6-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in ³	ISO 1183
Water Absorption	6.3 - 6.9 %	6.3 - 6.9 %	Saturation; ISO 62
Moisture Absorption at Equilibrium	1.8 - 2.2 %	1.8 - 2.2 %	23°C; 50% RH; ISO 62
Viscosity Measurement	135	135	ISO 307
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	restricted
Melt Flow	59.2 g/10 min @Load 5.00 kg, Temperature 275 °C	59.2 g/10 min @Load 11.0 lb, Temperature 527 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	70.0 MPa	10200 psi	50 mm/min; ISO 527-1/-2
Elongation at Yield	7.5 %	7.5 %	50 mm/min; ISO 527-1/-2
Modulus of Elasticity	4.30 GPa	624 ksi	ISO 527-1/-2
Flexural Strength	120 MPa	17400 psi	at max force; ISO 178
Izod Impact, Notched (ISO)	13.0 kJ/m ² @Temperature 23.0 °C	6.19 ft-lb/in ² @Temperature 73.4 °F	ISO 180/A
Charpy Impact Unnotched	7.00 J/cm ² @Temperature 23.0 °C	33.3 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	0.800 J/cm ² @Temperature 23.0 °C	3.81 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA
Tensile Creep Modulus, 1000 hours	1850 MPa @Strain <=0.500 %	268000 psi @Strain <=0.500 %	ISO 899-1

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.30 J/g-°C	0.311 BTU/lb-°F	
Thermal Conductivity	0.380 W/m-K	2.64 BTU-in/hr-ft²-°F	DIN 52612
Melting Point	220 °C	428 °F	DIN 53765
Maximum Service Temperature, Air	180 °C	356 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	IEC 60093
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	IEC 60093
Dielectric Constant	6.2 @Frequency 1.00 Hz	6.2 @Frequency 1.00 Hz	IEC 60250
Dissipation Factor	0.20 @Frequency 1.00e+6 Hz	0.20 @Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	400 V	400 V	Test solution A; IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	270 - 290 °C	518 - 554 °F	Injection-molding/Extrusion
Mold Temperature	80.0 - 90.0 °C	176 - 194 °F	Injection-molding

Descriptive Properties	Value	Comments
Color	BK 30564	
Commercial Status	Europe	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China