

BASF Ultramid® BU50I PA6 (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Description: Ultramid Ultratough Nylon BU50I is an unreinforced PA6, impact modified injection molding product that maintains its impact strength and ductility to -40 deg F (-40 deg C). The extreme low temperature tolerance of Ultratough Nylon BU50I makes it ideal for applications in which the weld line impact strength at low temperatures is critical. Applications: Automotive components, small engines, power tool parts and casings, cold weather and high impact supports gear, such as snowboards, ski components, helmets and hockey masks. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultramid-BU50I-PA6-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in³	ASTM D792
Moisture Absorption at Equilibrium	2.1 %	2.1 %	50% RH; ASTM D570
	7.3 %	7.3 %	Saturation; ASTM D570
Linear Mold Shrinkage	0.04572 cm/cm	0.04572 in/in	1/8" bar

Processing Properties	Metric	English	Comments
Melt Temperature	270 - 300 °C	518 - 572 °F	
Mold Temperature	60.0 - 85.0 °C	140 - 185 °F	
Dry Time	2 - 4 hour	2 - 4 hour	
Moisture Content	<= 0.15 %	<= 0.15 %	

Descriptive Properties	Value	Comments
Commercial Status	North America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China