

BASF Ultramid® C31 01 PA6/66

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66 , Nylon 66/6, Unreinforced

Material Notes:

Description: Ultramid® C31 01 is a copolyamide 6/66 grade of low viscosity that is well suited for the production of compounds and blends.

Product supplied in 2-2.5 mm CYLINDRICAL pellets.Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultramid-C31-01-PA666.php

Physical Properties	Metric	English	Comments
Bulk Density	0.690 - 0.710 g/cc	0.0249 - 0.0257 lb/in ³	
Density	1.12 g/cc	0.0405 lb/in ³	ISO 1183
Water Absorption	10.5 %	10.5 %	Saturation in water 23°C
Moisture Absorption at Equilibrium	3.2 %	3.2 %	23°C/50% RH
Viscosity Measurement	2.96 - 3.15	2.96 - 3.15	(RV) 1% [m/v] in 96% [m/m] sulfuric acid; ISO 307
	169 - 183	169 - 183	(RV) 0.5% [m/v] in 96% [m/m] sulfuric acid; ISO 307

Thermal Properties	Metric	English	Comments
Melting Point	195 - 198 °C	383 - 388 °F	ISO 3146
Decomposition Temperature	>= 300 °C	>= 572 °F	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.080 %	<= 0.080 %	ISO 15512

Descriptive Properties	Value	Comments
Commercial Status	Europe	
Extractables	<0.8 %	ISO 6427
Film Grade	1-3	BASF
Ignition Temperature	>400°C	ASTM D1929

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China