

BASF Ultramid® HMG14 HS BK 102 60% Glass Filled PA66 (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 60% Glass Fiber Filled

Material Notes:

Description: Ultramid HMG14 HS BK-102 is a 60% glass reinforced, injection molding grade of PA66 offering high strength and stiffness.

Due to inherently lower moisture absorption, Ultramid HMG14 HS BK-102 shows improved retention of mechanical properties after moisture conditioning. In addition, molded parts possess an exceptional surface finish. Applications: Ultramid HMG14 HS BK-102 was designed for applications requiring very high rigidity and should be considered for components that are constructed with metal. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultramid-HMG14-HS-BK-102-60-Glass-Filled-PA66-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.75 g/cc	0.0632 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	220 MPa	31900 psi	ISO 527
Tensile Modulus	20.83 GPa	3021 ksi	ISO 527
Flexural Strength	351 MPa	50900 psi	ISO 178
Flexural Modulus	19.4 GPa	2810 ksi	ISO 178
Izod Impact, Notched (ISO)	11.0 kJ/m ²	5.23 ft-lb/in ²	ISO 180
	13.0 kJ/m ²	6.19 ft-lb/in ²	ISO 180
Charpy Impact Unnotched	8.50 J/cm ²	40.4 ft-lb/in ²	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	9.30 J/cm ²	44.3 ft-lb/in ²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	280 - 305 °C	536 - 581 °F	
Mold Temperature	80.0 - 90.0 °C	176 - 194 °F	

Processing Properties	Metric ^{ur}	English ^{ur}	Comments
Moisture Content	<= 0.12 %	<= 0.12 %	

Descriptive Properties	Value	Comments
Color	BK 102	
Commercial Status	North America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China