

BLUESTAR 201-G30202 PBT, 30% Glass Filled

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

Material Notes:

Typical Applications: Energy saving lighting, E/E applications Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

http://www.lookpolymers.com/polymer_BLUESTAR-201-G30202-PBT-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.60 g/cc	1.60 g/cc	ASTM D792
Moisture Absorption at Equilibrium	0.16 %	0.16 %	50% RH; ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	ASTM D955
Melt Flow	16 g/10 min @Load 2.16 kg, Temperature 250 °C	16 g/10 min @Load 4.76 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	115 MPa	16700 psi	ASTM D638
Tensile Modulus	10.5 GPa	1520 ksi	ASTM D638
Flexural Strength	180 MPa	26100 psi	ASTM D790
Flexural Modulus	8.00 GPa	1160 ksi	ASTM D790
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	ASTM D256
Izod Impact, Unnotched (ISO)	60.0 kJ/m ²	28.6 ft-lb/in ²	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	208 °C	406 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 0.800 mm	V-0 @Thickness 0.0315 in	
	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.30e+16 ohm-cm	1.30e+16 ohm-cm	ASTM D257
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China