

BLUESTAR 201G25 PBT, 25% Glass Filled

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

Material Notes:

Typical Applications: Energy saving lighting Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

http://www.lookpolymers.com/polymer_BLUESTAR-201G25-PBT-25-Glass-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.56 g/cc	1.56 g/cc	ASTM D792
Moisture Absorption at Equilibrium	0.17 %	0.17 %	50% RH; ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	ASTM D955
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 250 °C	35 g/10 min @Load 4.76 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	110 MPa	16000 psi	ASTM D638
Flexural Strength	175 MPa	25400 psi	ASTM D790
Flexural Modulus	7.50 GPa	1090 ksi	ASTM D790
Izod Impact, Notched (ISO)	9.00 kJ/m ²	4.28 ft-lb/in ²	ASTM D256
Izod Impact, Unnotched (ISO)	55.0 kJ/m ²	26.2 ft-lb/in ²	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	210 °C	410 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 0.800 mm	V-0 @Thickness 0.0315 in	
	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
	V-0 @Thickness 3.20 mm	V-0 @Thickness 0.126 in	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China