

BNZ Materials BNZ-24 Insulating Firebrick

Category : Ceramic , Oxide , Silicon Oxide

Material Notes:

BNZ produces many types of Insulating Fire Brick (IFB) for use in applications from 2,000°F (1,093°C) to 3,200°F (1,760°C). Each type is formulated to meet specific thermal and physical requirements and after firing is machined to precise tolerances. Made from high purity refractory clays and other ceramic raw materials, these IFB contain a carefully graded organic filler which is burned out during manufacture to give a uniform controlled pore structure. Information provided by BNZ Materials Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BNZ-Materials-BNZ-24-Insulating-Firebrick.php

Physical Properties	Metric	English	Comments
Density	0.593 g/cc	0.0214 lb/in ³	ASTM C134
Deformation	0.00 % @Temperature 1093 °C, Time 5400 sec	0.00 % @Temperature 1999 °F, Time 1.50 hour	10 psi load, Hot Load Strength; ASTM C16

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.000800 GPa	0.116 ksi	ASTM C133
Compressive Strength	0.900 MPa	131 psi	Cold Crush Strength; ASTM C133

Thermal Properties	Metric	English	Comments
CTE, linear	5.60 µm/m-°C @Temperature 20.0 - 1093 °C	3.11 µin/in-°F @Temperature 68.0 - 1999 °F	
Thermal Conductivity	0.130 W/m-K @Temperature 260 °C	0.902 BTU-in/hr-ft ² -°F @Temperature 500 °F	ASTM C182
	0.160 W/m-K @Temperature 538 °C	1.11 BTU-in/hr-ft ² -°F @Temperature 1000 °F	ASTM C182
	0.200 W/m-K @Temperature 816 °C	1.39 BTU-in/hr-ft ² -°F @Temperature 1500 °F	ASTM C182
	0.230 W/m-K @Temperature 1093 °C	1.60 BTU-in/hr-ft ² -°F @Temperature 1999 °F	ASTM C182
Maximum Service Temperature, Air	1316 °C	2401 °F	Normal oxidizing atmosphere
	0.40 %	0.40 %	Permanent Linear Change; ASTM

Shrinkage Thermal Properties	@Temperature 1290 °C, Time 66400 sec	English @Temperature 2350 °F, Time 24.0 hour	C210 Comments
---------------------------------	---	--	------------------

Component Elements Properties	Metric	English	Comments
Al2O3	40 %	40 %	
CaO	10.3 %	10.3 %	
Fe2O3	0.50 %	0.50 %	
MgO	0.20 %	0.20 %	
Na2O	0.30 %	0.30 %	Includes K₂O
SiO2	47.2 %	47.2 %	
TiO2	1.5 %	1.5 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China