

BNZ Materials Color A Insulating Firebrick (French Grade)

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

BNZ produces many types of Insulating Fire Brick (IFB) for use in applications from 2,000°F (1,093°C) to 3,200°F (1,760°C). Each type is formulated to meet specific thermal and physical requirements and after firing is machined to precise tolerances. Made from high purity refractory clays and other ceramic raw materials, these IFB contain a carefully graded organic filler which is burned out during manufacture to give a uniform controlled pore structure. Information provided by BNZ Materials Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BNZ-Materials-Color-A-Insulating-Firebrick-French-Grade.php

Physical Properties	Metric	English	Comments
Density	0.820 g/cc	0.0296 lb/in ³	ASTM C134

Mechanical Properties	Metric	English	Comments
Compressive Strength	2.50 MPa	363 psi	Cold Crush Strength; ASTM C133

Thermal Properties	Metric	English	Comments
CTE, linear	6.30 µm/m-°C	3.50 µin/in-°F	
	@Temperature 20.0 - 1000 °C	@Temperature 68.0 - 1830 °F	
Thermal Conductivity	0.210 W/m-K	1.46 BTU-in/hr-ft ² -°F	ASTM C182
	@Temperature 200 °C	@Temperature 392 °F	
	0.240 W/m-K	1.67 BTU-in/hr-ft ² -°F	ASTM C182
	@Temperature 400 °C	@Temperature 752 °F	
	0.280 W/m-K	1.94 BTU-in/hr-ft ² -°F	ASTM C182
	@Temperature 600 °C	@Temperature 1110 °F	
	0.320 W/m-K	2.22 BTU-in/hr-ft ² -°F	ASTM C182
	@Temperature 800 °C	@Temperature 1470 °F	
	0.370 W/m-K	2.57 BTU-in/hr-ft ² -°F	ASTM C182
	@Temperature 1000 °C	@Temperature 1830 °F	
Maximum Service Temperature, Air	1350 °C	2460 °F	
Shrinkage	0.50 %	0.50 %	Permanent Linear Change; ASTM C210
	@Temperature 1350 °C, Time 43200 sec	@Temperature 2460 °F, Time 12.0 hour	

Descriptive Properties	Value	Comments
Composition (%)	0.6	CaO + MgO
	2.3	Fe ₂ O ₃ + TiO ₂
	4.5	Na ₂ O + K ₂ O
	92.4	Al ₂ O ₃ + SiO ₂

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China