

## BYK Cloisite® 25A Nanoclay

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer

### Material Notes:

Cloisite® 25A is an additive for plastics to improve various plastic physical properties, such as reinforcement, HDT, CLTE and barrier. Information provided by Southern Clay Products Southern Clay Products is now a part of BYK Additives.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BYK-Cloisite-25A-Nanoclay.php](http://www.lookpolymers.com/polymer_BYK-Cloisite-25A-Nanoclay.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.87 g/cc	1.87 g/cc	
Bulk Density	0.1935 g/cc	0.006991 lb/in <sup>3</sup>	Loose
	0.3281 g/cc	0.01185 lb/in <sup>3</sup>	Packed
Loss On Ignition	34 %	34 %	
Particle Size	<= 2.0 µm	<= 2.0 µm	10%
	<= 6.0 µm	<= 6.0 µm	50%
	<= 13 µm	<= 13 µm	90%

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	83	83	5% Cloisite® reinforced Nylon 6
Tensile Strength, Ultimate	101 MPa	14600 psi	5% Cloisite® reinforced Nylon 6
Elongation at Break	8.0 %	8.0 %	5% Cloisite® reinforced Nylon 6
Modulus of Elasticity	4.657 GPa	675.5 ksi	5% Cloisite® reinforced Nylon 6
Flexural Modulus	3.78 GPa	548 ksi	5% Cloisite® reinforced Nylon 6
Izod Impact, Notched	0.270 J/cm	0.506 ft-lb/in	5% Cloisite® reinforced Nylon 6

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	96.0 °C	205 °F	5% Cloisite® reinforced Nylon 6

Processing Properties	Metric	English	Comments
Moisture Content	<= 2.0 %	<= 2.0 %	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Modifier Concentration, meq/ 100g clay Descriptive Properties	95 Value	Comments
Organic Modifier	dimethyl, hydrogenated tallow, 2-ethylhexyl quaternary ammonium	
X-Ray Diffraction d-Spacing (001)	18.6 Angstroms	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China