

Bapolene® 3295 Polyethylene, Injection Grade

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

Designed to offer improved cycle times and dimensional stability This product complies with US FDA 21CFR177.1250.Applications: Food containers and closures.Bapolene® and Bapolan® are registered trademarks of Bamberger Polymers, Inc. Information provided by Bamberger Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bapolene-3295-Polyethylene-Injection-Grade.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ASTM D1505
Melt Flow	50 g/10 min @Load 2.16 kg, Temperature 190 °C	50 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	23.0 MPa	3340 psi	ASTM D638
Flexural Modulus	1.00 GPa	145 ksi	Tangent; ASTM D790A

Descriptive Properties	Value	Comments
Process	Injection Molding	
Region	Europe/Turkey	Bamberger Polymers Distribution
	International	Bamberger Polymers Distribution
	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China