

Barlog Plastics KEBABLEND W/H 23.10.1 PBT functional compound, high density

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

PBT mod.Information provided by BARLOG plastics GmbH.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBABLEND-WH-23101-PBT-functional-compound-high-density.php

Physical Properties	Metric	English	Comments
Density	2.30 g/cc	0.0831 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	36.0 MPa	5220 psi	ISO 527-1
Elongation at Break	10 %	10 %	ISO 527-1
Tensile Modulus	3.00 GPa	435 ksi	ISO 527-1
Charpy Impact Unnotched	2.50 J/cm ²	11.9 ft-lb/in ²	ISO 179-1eU
Charpy Impact, Notched	0.250 J/cm ²	1.19 ft-lb/in ²	ISO 179-1eA

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	10°C/min; ISO 11357-1/-3

Descriptive Properties	Value	Comments
Resin Type	PBT mod.	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China