

## Barlog Plastics KEBAFLEX S 65 A.02 TPE-S, Shore A65, translucent

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE

### Material Notes:

TPE-SInformation provided by BARLOG plastics GmbH.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Barlog-Plastics-KEBAFLEX-S-65-A02-TPE-S-Shore-A65-translucent.php](http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBAFLEX-S-65-A02-TPE-S-Shore-A65-translucent.php)

| Physical Properties               | Metric      | English                   | Comments  |
|-----------------------------------|-------------|---------------------------|-----------|
| Density                           | 0.900 g/cc  | 0.0325 lb/in <sup>3</sup> | ISO 1183  |
| Linear Mold Shrinkage, Flow       | 0.018 cm/cm | 0.018 in/in               | ISO 294-4 |
| Linear Mold Shrinkage, Transverse | 0.010 cm/cm | 0.010 in/in               | ISO 294-4 |

| Mechanical Properties     | Metric   | English  | Comments  |
|---------------------------|----------|----------|-----------|
| Hardness, Shore A         | 65       | 65       |           |
| Tensile Strength at Break | 9.70 MPa | 1410 psi | ISO 527-1 |
| Elongation at Break       | 700 %    | 700 %    | ISO 527-1 |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Resin Type             | TPE-S |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China