

Barlog Plastics KEBAFORM C 902 CF POM Copolymer, carbon fiber reinforced, electr. conductive

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Carbon Fiber Filled

Material Notes:

POM-CF10 Information provided by BARLOG plastics GmbH.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBAFORM-C-902-CF-POM-Copolymer-carbon-fiber-reinforced-electr-conductive.php

Physical Properties	Metric	English	Comments
Density	1.43 g/cc	0.0517 lb/in ³	ISO 1183
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 190 °C	12 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	ISO 527-1
Elongation at Break	4.0 %	4.0 %	ISO 527-1
Tensile Modulus	6.60 GPa	957 ksi	ISO 527-1
Charpy Impact, Notched	0.450 J/cm ²	2.14 ft-lb/in ²	ISO 179-1eA

Thermal Properties	Metric	English	Comments
Melting Point	166 °C	331 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	160 °C	320 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1e+05	1e+05	IEC 60093
Surface Resistance	10000 ohm	10000 ohm	IEC 60093

Descriptive Properties	Value	Comments
Resin Type	POM-CF10	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China