

Barlog Plastics KEBAFORM C 902 TF POM Copolymer unreinforced, improved wear and friction

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

POM Information provided by BARLOG plastics GmbH.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBAFORM-C-902-TF-POM-Copolymer-unreinforced-improved-wear-and-friction.php

Physical Properties	Metric	English	Comments
Density	1.51 g/cc	0.0546 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.20 %	0.20 %	similar to ISO 62 test
Melt Flow	7.5 g/10 min @Load 2.16 kg, Temperature 190 °C	7.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	48.0 MPa	6960 psi	ISO 527-1
Elongation at Yield	7.0 %	7.0 %	ISO 527-1
Tensile Modulus	2.30 GPa	334 ksi	ISO 527-1
Charpy Impact, Notched	0.300 J/cm ²	1.43 ft-lb/in ²	ISO 179-1eA

Thermal Properties	Metric	English	Comments
Melting Point	166 °C	331 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ISO 75-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+15 ohm-cm	2.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093

Descriptive Properties	Value	Comments
Resin Type	POM	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China