

Bedford Plastics Glass Reinforced Vinylester Flat Sheet, 3/8" to 1"

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Vinyl Ester , Vinyl Ester Sheet Molding Compound

Material Notes:

Flame retardant grade; see details in the property table. Pultrusion results in the production and supply of one of the worlds strongest and most durable products available today. The pultruded products feature: High Strength Corrosion Resistant to many chemicals Light Weight - Weighs nearly 80% less than a steel profile of similar dimension Electrically Non-Conductive Non-Metallic Lower Life Cycle Cost Non-Leaching. Environmentally Friendly Dimensional Stability Information provided by Bedford Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bedford-Plastics-Glass-Reinforced-Vinylester-Flat-Sheet-38-to-1.php

Physical Properties	Metric	English	Comments
Density	1.72 - 1.94 g/cc	0.0620 - 0.0700 lb/in ³	ASTM D792
Water Absorption	<= 0.60 %	<= 0.60 %	24 hrs; ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	40	40	ASTM D2583
Tensile Strength, Ultimate	68.9 MPa	10000 psi	Crosswise; ASTM D638
	165 MPa	24000 psi	Lengthwise; ASTM D638
Tensile Modulus	9.65 GPa	1400 ksi	Crosswise; ASTM D638
	13.8 GPa	2000 ksi	Lengthwise; ASTM D638
Flexural Strength	124 MPa	18000 psi	Crosswise; ASTM D790
	207 MPa	30000 psi	Lengthwise; ASTM D790
Flexural Modulus	9.65 GPa	1400 ksi	Crosswise; ASTM D790
	13.8 GPa	2000 ksi	Lengthwise; ASTM D790
Compressive Strength	121 MPa	17500 psi	Crosswise; ASTM D635
	165 MPa	24000 psi	Lengthwise; ASTM D635
Compressive Modulus	6.89 GPa	1000 ksi	Crosswise; ASTM D635
	12.4 GPa	1800 ksi	Lengthwise; ASTM D635
Ultimate Bearing Strength	221 MPa	32000 psi	Lengthwise; ASTM D953
Shear Strength	41.4 MPa	6000 psi	Perpendicular Shear Stress, Lengthwise; ASTM D3946
	41.4 MPa	6000 psi	Perpendicular Shear Stress,

Mechanical Properties	Metric	English	Crosswise: ASTM D3946 Comments
Izod Impact, Notched	2.67 J/cm	5.00 ft-lb/in	Crosswise; ASTM D256
	10.7 J/cm	20.0 ft-lb/in	Lengthwise; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	8.00 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$ @Temperature 20.0 $^{\circ}\text{C}$	4.44 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$ @Temperature 68.0 $^{\circ}\text{F}$	Lengthwise; ASTM D696
Flammability, UL94	V-0	V-0	
Flame Spread Index	≤ 25	≤ 25	Tunnel Test; ASTM E84
NBS Smoke Density	600 - 700	600 - 700	ASTM E662

Electrical Properties	Metric	English	Comments
Dielectric Strength	1.38 kV/mm	35.0 kV/in	Lengthwise; ASTM D149
	7.87 kV/mm	200 kV/in	Perpendicular to Laminate Face; ASTM D149
Arc Resistance	120 sec	120 sec	Lengthwise; ASTM D495

Descriptive Properties	Value	Comments
Flammability	Nonburning	ASTM D635

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China