

Beijing Chemical Industry KAIFA® HN201-G0 PA6 Resin

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Good flow Information provided by Beijing Chemical Industry Research Institute (Group)

Order this product through the following link:

http://www.lookpolymers.com/polymer_Beijing-Chemical-Industry-KAIFA-HN201-G0-PA6-Resin.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.015 - 0.020 cm/cm	0.015 - 0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	62.0 MPa	8990 psi	ASTM D638
Flexural Strength	88.0 MPa	12800 psi	ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	ASTM D790
Izod Impact, Notched	0.500 J/cm @Thickness 3.20 mm	0.937 ft-lb/in @Thickness 0.126 in	ASTM D256
Charpy Impact Unnotched	>= 10.0 J/cm ²	>= 47.6 ft-lb/in ²	ISO179
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	ISO179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Constant	3.1 @Frequency 1e+6 Hz	3.1 @Frequency 1e+6 Hz	ASTM D150
Dielectric Strength	21.0 kV/mm @Thickness 2.00 mm	533 kV/in @Thickness 0.0787 in	ASTM D149

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	200 - 210 °C	392 - 410 °F	
Middle Barrel Temperature			

Processing Properties	230 - 240 °C Metric	446 - 464 °F English	Comments
Front Barrel Temperature	235 - 245 °C	455 - 473 °F	
Nozzle Temperature	235 - 240 °C	455 - 464 °F	
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	
Drying Temperature	130 °C	266 °F	
Dry Time	4 hour	4 hour	
Injection Pressure	60.0 - 90.0 MPa	8700 - 13100 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China