

Bhansali Engineering Abstron IM-17A ABS Injection Molding Grade

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Medium Impact, High Gloss, High Flow Information provided by Bhansali

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bhansali-Engineering-Abstron-IM-17A-ABS-Injection-Molding-Grade.php

Physical Properties	Metric	English	Comments
Density	1.045 g/cc	0.03775 lb/in ³	ASTM D-792
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D-955
Melt Flow	45 g/10 min	45 g/10 min	ASTM D-1238
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	112	112	ASTM D-785
Tensile Strength, Yield	43.1 MPa	6260 psi	Type 1; ASTM D-638
	@Thickness 3.20 mm	@Thickness 0.126 in	
Flexural Yield Strength	61.8 MPa	8960 psi	ASTM D-790
	@Thickness 6.40 mm	@Thickness 0.252 in	
Flexural Modulus	2.21 GPa	320 ksi	ASTM D-790
	@Thickness 6.40 mm	@Thickness 0.252 in	
Izod Impact, Notched	1.67 J/cm	3.12 ft-lb/in	ASTM D-256
	@Thickness 6.40 mm	@Thickness 0.252 in	
	2.0588 J/cm	3.8570 ft-lb/in	ASTM D-256
	@Thickness 3.20 mm	@Thickness 0.126 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	93.0 °C	199 °F	Method A - Annealed; ASTM D-648
Vicat Softening Point	103 °C	217 °F	Method B; ASTM D-1525
Flammability, UL94	HB	HB	UL-94
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China