

Borealis BG373MO Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

BG373MO is a heterophasic copolymer. Products molded with this grade exhibit excellent antistatic performance and very good mould release. Electrostatic charge is

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-BG373MO-Polypropylene-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.010 - 0.020 cm/cm	0.010 - 0.020 in/in	
Melt Flow	30 g/10 min @Load 2.16 kg, Temperature 230 °C	30 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	88	88	ISO 2309-2
Tensile Strength, Yield	27.0 MPa	3920 psi	50mm/min; ISO 527-2
Elongation at Yield	5.0 %	5.0 %	50mm/min; ISO 527-2
Tensile Modulus	1.55 GPa	225 ksi	1mm/min; ISO 527-2
Charpy Impact, Notched	0.400 J/cm ² @Temperature -20.0 °C	1.90 ft-lb/in ² @Temperature -4.00 °F	ISO 179/1eA
	0.700 J/cm ² @Temperature 23.0 °C	3.33 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA
Puncture Energy	20.0 J @Temperature -20.0 °C	14.8 ft-lb @Temperature -4.00 °F	ISO 6603-2
	24.0 J @Temperature 0.000 °C	17.7 ft-lb @Temperature 32.0 °F	ISO 6603-2

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	103 °C	217 °F	ISO 75-2

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Melt Temperature Processing Properties	210 - 260 °C Metric	410 - 500 °F English	Comments
Mold Temperature	10.0 - 30.0 °C	50.0 - 86.0 °F	
Hold Pressure	20.0 - 50.0 MPa	2900 - 7250 psi	

Descriptive Properties	Value	Comments
Injection Velocity	highest possible	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China