

## Borealis BorPURE™ RD208CF Polypropylene Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

### Material Notes:

BorPure™ RD208CF is a random copolymer. This grade is suitable for the manufacturing of unoriented films on chill roll processes. This grade is suitable for the manufacturing of unoriented films on chill roll processes. Applications: BorPure™ RD208CF is recommended for food packaging, high quality stationery film, lamination films, textile packaging film, sealing layer in coextrusion. Information provided by Borealis AG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Borealis-BorPURE-RD208CF-Polypropylene-Random-Copolymer.php](http://www.lookpolymers.com/polymer_Borealis-BorPURE-RD208CF-Polypropylene-Random-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.900 - 0.910 g/cc	0.0325 - 0.0329 lb/in <sup>3</sup>	ISO 1183
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	550 - 750 %	550 - 750 %	ISO 527-3
Tensile Modulus	0.350 - 0.450 GPa	50.8 - 65.3 ksi	MD/TD; ISO 527-3
Flexural Modulus	0.650 GPa	94.3 ksi	ISO 178
Dart Drop, Total Energy	23.0 J @Thickness 0.0500 mm	17.0 ft-lb @Thickness 0.00197 in	1180 N; ISO 7765-2
Coefficient of Friction	>= 0.50	>= 0.50	film to film; ISO 8295
Film Tensile Strength at Break, MD	30.0 - 50.0 MPa	4350 - 7250 psi	ISO 527-3
Film Tensile Strength at Break, TD	25.0 - 45.0 MPa	3630 - 6530 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Melting Point	138 - 142 °C	280 - 288 °F	DSC; ISO 3146
Vicat Softening Point	122 °C @Load 1.02 kg	252 °F @Load 2.25 lb	A50; ISO 306

Optical Properties	Metric	English	Comments
Haze	<= 1.8 %	<= 1.8 %	ASTM D1003

Gloss Optical Properties	$\geq 120\%$ Metric	$\geq 120\%$ English	20° of arc: ASTM D2457 Comments
-----------------------------	------------------------	-------------------------	------------------------------------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China