

## Borealis Borecene™ RM8343RC Linear Polyethylene for Rotational Molding

Category: Polymer, Thermoplastic, Polyethylene (PE), MDPE, Medium Density Polyethylene (MDPE), Rotational Molded

## **Material Notes:**

Borecene RM8343RC is a third generation linear medium density natural polyethylene for rotational molding. Borecene RM8343RC is a special grade, which has passed many rigorous tests and can be considered as a possible replacement for crosslinkable polyethylene in many applications. The narrow molecular weight distribution imparted through metallocene catalyst technology provides an ideal balance of flow and physical properties. Borecene RM8343RC is delivered as powder.Borecene RM8343RC can be considered as a possible replacement for crosslinkable products in rotational molding such as fuel tanks and tanks.Information provided by the Manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Borealis-Borecene-RM8343RC-Linear-Polyethylene-for-Rotational-Molding.php

Physical Properties	Metric	English	Comments
Density	0.934 g/cc	0.0337 lb/in³	ASTM D1505
ESCR 10% Igepal®	>= 300 hour	>= 300 hour	ARM Method
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	17.9 MPa	2600 psi	At 50 mm/min; ASTM D683 IV
Flexural Modulus	0.490 GPa	71.0 ksi	At 2 mm/min; ASTM D790
Dart Drop Total Energy	210.0 J/cm	0.3934 ft-lb/mil	(-4oF/-20°C); ASTM D3763
Dart Drop	152 g/micron	3860 g/mil	Instrumented Falling Weight (-4°F/- 20°C); ASTM D3763

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	65.0 °C	149 °F	ASTM D648
Brittleness Temperature	<= -70.0 °C	<= -94.0 °F	ASTM D746

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China