

## Borealis Borflow™ HL508FB Polypropylene Homopolymer

Category: Polymer, Thermoplastic, Polypropylene (PP), Polypropylene, Molded

## **Material Notes:**

Borflow HL508FB is a polypropylene homopolymer grade intended for fiber applications characterized by narrow molecular weight distribution, controlled rheology, easy processability, optimal product consistency, very high flow, and perfect suitable for electrostatic charging. Borflow HL508FB is designed for the production of micro denier fibers at high spinning speeds and typical for meltblown applications. Information provided by the Manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Borealis-Borflow-HL508FB-Polypropylene-Homopolymer.php

| Physical Properties | Metric                               | English                              | Comments |
|---------------------|--------------------------------------|--------------------------------------|----------|
| Melt Flow           | 800 g/10 min                         | 800 g/10 min                         | ISO 1133 |
|                     | @Load 2.16 kg,<br>Temperature 230 °C | @Load 4.76 lb,<br>Temperature 446 °F |          |

| Thermal Properties | Metric       | English      | Comments |
|--------------------|--------------|--------------|----------|
| Melting Point      | 156 - 160 °C | 313 - 320 °F | ISO 3146 |

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China