

Borealis FG5224 Linear Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Film Grade

Material Notes:

FG5224 is a Butene Linear Low Density Polyethylene for Film Extrusion. Includes antioxidant, anti-block and medium slip additives. This grade is developed for production of lamination film. FG5224 has good heat sealing properties and hot tack strength. By mixing with FG5223 any desired level of friction can be obtained. Applications FG5224 has been developed especially for applications like: lamination films, shrink film, carrier-bag film, and food wrap film. Information provided by Borealis AG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-FG5224-Linear-Low-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.922 g/cc	0.0333 lb/in ³	ISO 1183
Melt Flow	0.90 g/10 min @Load 2.16 kg, Temperature 190 °C	0.90 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133
Antiblock Level	625 ppm	625 ppm	Borealis Method
Slip Level	480 ppm	480 ppm	erucamide; Borealis Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	12.0 MPa	1740 psi	MD/TD; ISO 527-3
Film Elongation at Break, MD	800 %	800 %	ISO 527-3
Film Elongation at Break, TD	1000 %	1000 %	ISO 527-3
Tensile Modulus	0.145 GPa	21.0 ksi	MD; ASTM D882-A
	0.165 GPa	23.9 ksi	TD; ASTM D882-A
Coefficient of Friction	0.10	0.10	Dynamic; ISO 8295
Elmendorf Tear Strength, MD	2.91 g/micron	73.9 g/mil	ISO 6383/2
Elmendorf Tear Strength, TD	13.11 g/micron	333.0 g/mil	ISO 6383/2
Dart Drop Test	260 g @Thickness 0.0700 mm	0.573 lb @Thickness 0.00276 in	ISO 7765-1
Film Tensile Strength at Break, MD	29.0 MPa	4210 psi	ISO 527-3
Film Tensile Strength at Break, TD	28.0 MPa	4060 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Melting Point	122 °C	252 °F	ISO 11357-3

Optical Properties	Metric	English	Comments
Haze	10 %	10 %	ASTM D1003
Gloss	100 %	100 %	ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China