

Bostik 2105 Low viscosity, short open time EVA Glue Stick

Category : Polymer , Adhesive , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Adhesive/Sealant Grade

Material Notes:

Bostik 2105 Low viscosity, short open time EVA Glue StickLow viscosity. Short open time for woodworking and packaging applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bostik-2105-Low-viscosity-short-open-time-EVA-Glue-Stick.php

Physical Properties	Metric	English	Comments
Viscosity	1830 cP	1830 cP	Typical
	@Temperature 177 °C	@Temperature 350 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	65.6 °C	150 °F	
Minimum Service Temperature, Air	-28.9 °C	-20.0 °F	

Processing Properties	Metric	English	Comments
Pot Life	0.083 - 0.17 min	0.083 - 0.17 min	Open Time

Descriptive Properties	Value	Comments
Color	Straw	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China