

Braskem TR3350CW Random Copolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Description: Excellent mold release, superior color and processing stability, high melt flow, excellent processability, clarified. Applications:

Suggested uses include housewares, fast-cycle injection molding. Process: Injection Molding This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA – Food and Drugs Administration. The additives present are covered in appropriate regulation by FDA. Information provided by Braskem

Order this product through the following link:

http://www.lookpolymers.com/polymer_Braskem-TR3350CW-Random-Copolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Melt Flow	31 g/10 min @Load 2.16 kg, Temperature 230 °C	31 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	28.3 MPa	4100 psi	2 in/min; ASTM D638
Elongation at Yield	11 %	11 %	2 in/min; ASTM D638
Flexural Modulus	1.00 GPa	145 ksi	0.05 in/min, 1% secant; ASTM D-790A
Izod Impact, Notched	0.374 J/cm	0.700 ft-lb/in	ASTM D256A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China