

Bulk Molding Compounds BMC 1901 Mineral Filled Alkyd

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Polyester, TS , Alkyd (Polyester), Molded, Mineral Filler

Material Notes:

BMC 1901 molding compound is a mineral filled, glass-fiber-reinforced alkyd compound suitable for compression transfer molding. It is a general purpose with medium impact strength and good overall electrical properties. Typical applications include switch components, relay bases, stack insulator s and as a formable insulating putty for motor construction and repair.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bulk-Molding-Compounds-BMC-1901-Mineral-Filled-Alkyd.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.21 g/cc	2.21 g/cc	
Water Absorption	0.28 %	0.28 %	24 hours, 23°C
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	60 - 80	60 - 80	
Flexural Strength	103 - 138 MPa	15000 - 20000 psi	
Compressive Strength	152 - 179 MPa	22000 - 26000 psi	
Izod Impact, Notched	1.07 - 2.14 J/cm	2.00 - 4.00 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	>= 260 °C	>= 500 °F	
Flammability, UL94	HB	HB	
	@Thickness 6.35 mm	@Thickness 0.250 in	
	HB	HB	
	@Thickness 3.17 mm	@Thickness 0.125 in	
	HB	HB	
	@Thickness 1.59 mm	@Thickness 0.0625 in	

Electrical Properties	Metric	English	Comments
Dielectric Constant	7.3	7.3	
	@Frequency 60 Hz	@Frequency 60 Hz	
Dielectric Strength	12.8 kV/mm	325 kV/in	Short Time

Electrical Properties	Metric	English	Comments
Dissipation Factor	@Frequency 60 Hz	@Frequency 60 Hz	
Arc Resistance	>= 180 sec	>= 180 sec	
Comparative Tracking Index	>= 600 V	>= 600 V	

Processing Properties	Metric	English	Comments
Mold Temperature	138 - 166 °C	280 - 330 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China