

CLAL-MSX DECLAFOR® 1015 TH1 Wire quenched/Precipitation Heat Treated Copper Alloy

Category : Metal , Nonferrous Metal , Copper Alloy

Material Notes:

Main Characteristic: Age hardening alloy Beryllium free alloy Good machinability High mechanical properties Typical Applications: Coaxial connectors Spectacles parts Sliding contacts parts All kind of turned parts Information provided by CLAL-MSX

Order this product through the following link:

http://www.lookpolymers.com/polymer_CLAL-MSX-DECLAFOR-1015-TH1-Wire-quenchedPrecipitation-Heat-Treated-Copper-Alloy.php

Physical Properties	Metric	English	Comments
Density	8.80 g/cc	0.318 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	240 - 280	240 - 280	
Tensile Strength, Ultimate	800 - 850 MPa	116000 - 123000 psi	
Tensile Strength, Yield	650 - 760 MPa @Strain 0.200 %	94300 - 110000 psi @Strain 0.200 %	
Elongation at Break	>= 10 %	>= 10 %	Alo 100 mm
Modulus of Rigidity	115 GPa	16700 ksi	Torsion

Thermal Properties	Metric	English	Comments
CTE, linear	17.2 µm/m-°C @Temperature 0.000 - 200 °C	9.56 µin/in-°F @Temperature 32.0 - 392 °F	
Thermal Conductivity	55.0 W/m-K	382 BTU-in/hr-ft ² -°F	
Melting Point	960 °C	1760 °F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	87 %	87 %	
Nickel, Ni	7.5 %	7.5 %	
Other	0.50 %	0.50 %	
Tin, Sn	5.0 %	5.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000130 ohm-cm	0.0000130 ohm-cm	

Descriptive Properties	Value	Comments
Color	Pinky roseate	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China