

CMW® D55X Post-oxidized Silver Cadmium Oxide Contact Material ASTM B781, Table 3

Category : Metal , Metal Matrix Composite , Nonferrous Metal , Precious Metal , Silver Alloy

Material Notes:

For electrical contacts; resistant to welding and high surge currents
Information provided by CMW Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_CMW-D55X-Post-oxidized-Silver-Cadmium-Oxide-Contact-Material-ASTM-B781-Table-3.php

Physical Properties	Metric	English	Comments
Density	10.02 g/cc	0.3620 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell F	50 - 85	50 - 85	50 (annealed) - 85 (worked)
Tensile Strength, Ultimate	207 MPa	30000 psi	Annealed
	269 MPa	39000 psi	Worked

Thermal Properties	Metric	English	Comments
Melting Point	<= 980 °C	<= 1800 °F	
Liquidus	980 °C	1800 °F	

Component Elements Properties	Metric	English	Comments
CdO	15 %	15 %	
Silver, Ag	85 %	85 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000246 ohm-cm	0.00000246 ohm-cm	(70% IACS)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China