

C.O.I.M. EXTER S® S 101 Orthophthalic Resin

Category : Polymer , Thermoset , Polyester, TS , Polyester (Thermoset) - Rigid

Material Notes:

Description: The Exter S product line contains a large number of unsaturated polyester resin products with an array of properties and applications. Specific Notes for EXTER S® S 101: Medium/high reactivity resin suitable for the production of tanks. Information provided by P.A.T. Products, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_COIM-EXTER-S-S-101-Orthophthalic-Resin.php

Physical Properties	Metric	English	Comments
Brookfield Viscosity	760 - 960 cP	760 - 960 cP	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 - 95.0 °C	194 - 203 °F	

Chemical Properties	Metric	English	Comments
Styrene Content	32 - 34 %	32 - 34 %	

Descriptive Properties	Value	Comments
Rigidity	medium/low	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China