

## C.O.I.M. EXTER S® S 801 Neopentylic Resin

Category: Polymer, Thermoset, Polyester, TS, Polyester (Thermoset) - Rigid

## **Material Notes:**

Description: The Exter S product line contains a large number of unsaturated polyester resin products with an array of properties and applications. Specific Notes for ESTER S® S 801: Resin for gel-coats and high-quality manufactured items Information provided by P.A.T. Products, Inc.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_COIM-EXTER-S-S-801-Neopentylic-Resin.php

Physical Properties	Metric	English	Comments
Brookfield Viscosity	500 - 700 cP	500 - 700 cP	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	100 °C	212 °F	

Chemical Properties	Metric	English	Comments
Styrene Content	39 - 41 %	39 - 41 %	

Descriptive Properties	Value	Comments
Rigidity	medium	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China