

CP-Polymer-Technik Wellamid® 6000 GX 350 HWCP Combination Nylon 6, Heat Stabilized, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-6000-GX-350-HWCP-Combination-Nylon-6-Heat-Stabilized-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.8 - 2.3 %	1.8 - 2.3 %	23°C/50%RH, Starting when dry; DIN 53495
Linear Mold Shrinkage	0.0050 cm/cm @Thickness 4.00 mm	0.0050 in/in @Thickness 0.157 in	
Linear Mold Shrinkage, Transverse	0.0070 cm/cm @Thickness 4.00 mm	0.0070 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	40.0 MPa	5800 psi	5 mm/min; ISO 527
Elongation at Break	10 %	10 %	5 mm/min; ISO 527
Tensile Modulus	2.70 GPa	392 ksi	ISO 527
Charpy Impact Unnotched	9.00 J/cm ² @Temperature 23.0 °C	42.8 ft-lb/in ² @Temperature 73.4 °F	ISO 179
Charpy Impact, Notched	1.60 J/cm ² @Temperature 23.0 °C	7.61 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	215 °C	419 °F	Kofler

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 93
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	ISO 3915
	7.0	7.0	

Dielectric Constant Electrical Properties	Metric @ Frequency 1e+6 Hz	English @ Frequency 1e+6 Hz	IEC 250 Comments
Dielectric Strength	35.0 kV/mm	889 kV/in	IEC 243-1
Dielectric Loss Index	0.10	0.10	At 1 MHz; IEC 250

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 290 °C	482 - 554 °F	
Mold Temperature	80.0 - 100 °C	176 - 212 °F	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Holding Pressure	Medium	
Injection Speed	Medium to High	
Screw Speed	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China