

CP-Polymer-Technik Wellamid® 6600 GV 5 HWCP 5% Glass Fiber Nylon 66, Heat Stabilized, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Glass Fiber Filled

Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-6600-GV-5-HWCP-5-Glass-Fiber-Nylon-66-Heat-Stabilized-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	2.2 - 3.0 %	2.2 - 3.0 %	23°C/50%RH, Starting when dry; DIN 53495
Linear Mold Shrinkage	0.0050 cm/cm @Thickness 4.00 mm	0.0050 in/in @Thickness 0.157 in	
Linear Mold Shrinkage, Transverse	0.010 cm/cm @Thickness 4.00 mm	0.010 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	5 mm/min; ISO 527
Elongation at Break	7.0 %	7.0 %	5 mm/min; ISO 527
Tensile Modulus	2.20 GPa	319 ksi	ISO 527
Charpy Impact Unnotched	4.50 J/cm ² @Temperature 23.0 °C	21.4 ft-lb/in ² @Temperature 73.4 °F	ISO 179
Charpy Impact, Notched	0.900 J/cm ² @Temperature 23.0 °C	4.28 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	255 °C	491 °F	Kofler

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 93
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	ISO 3915
	6.0	6.0	

Dielectric Constant Electrical Properties	Metric @ Frequency 1e+6 Hz	English @ Frequency 1e+6 Hz	IEC 250 Comments
Dielectric Strength	35.0 kV/mm	889 kV/in	IEC 243-1
Dielectric Loss Index	0.15	0.15	At 1 MHz; IEC 250

Processing Properties	Metric	English	Comments
Melt Temperature	265 - 295 °C	509 - 563 °F	
Mold Temperature	70.0 - 100 °C	158 - 212 °F	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Holding Pressure	High	
Injection Speed	High	
Screw Speed	Medium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China