

CTC SunPro® SP 200 TF 3033 Polypropylene Copolymer, 33% Talc Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

SunPro® SP 200 TF 3033 is a 33% talc filled polypropylene copolymer. It has applications in automotive wheel housings and general purpose automotive. Automotive Application: VW TL 52660 MD 03Data provided by Composite Technologies (CTC).

Order this product through the following link:

http://www.lookpolymers.com/polymer_CTC-SunPro-SP-200-TF-3033-Polypropylene-Copolymer-33-Talc-Filled.php

Physical Properties	Metric	English	Comments
Melt Flow	15 g/10 min	15 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	15.0 MPa	2180 psi	ISO 527-1/2
Flexural Modulus	1.40 GPa	203 ksi	0.05 in/min; ISO 178
Izod Impact, Notched (ISO)	40.0 kJ/m ²	19.0 ft-lb/in ²	Low Temp; ISO 180/1eA

Descriptive Properties	Value	Comments
Talc Content (%)	Ash	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China