

Carmel Olefins CAPILENE® SL 50 Polypropylene Impact Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

Material Notes:

Description: CAPILENE® SL 50 is a medium melt flow rate impact copolymer for injection molding applications. This grade combines good stiffness and impact properties. Applications: CAPILENE® SL 50 is suitable for injection molding of crates, battery cases and technical articles. Information provided by Carmel Olefins.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Carmel-Olefins-CAPILENE-SL-50-Polypropylene-Impact-Copolymer.php

Physical Properties	Metric	English	Comments
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.0 MPa	3920 psi	50 mm/min; ASTM D638
Elongation at Yield	12 %	12 %	50 mm/min; ASTM D638
Flexural Modulus	1.25 GPa	181 ksi	ASTM D790
Izod Impact, Notched	0.500 J/cm	0.937 ft-lb/in	ASTM D256
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	1.20 J/cm	2.25 ft-lb/in	ASTM D256
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	88.0 °C	190 °F	ASTM D648
Vicat Softening Point	150 °C	302 °F	ASTM D1525
	@Load 1.02 kg	@Load 2.25 lb	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

