

CeramTec V 679 Alumina, 99.7%

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Aluminas exhibit good mechanical properties such as hardness, compressive and tensile strength, and elastic modulus. They perform well at elevated temperatures.

Order this product through the following link:

http://www.lookpolymers.com/polymer_CeramTec-V-679-Alumina-997.php

Physical Properties	Metric	English	Comments
Density	3.90 g/cc	0.141 lb/in ³	DIN EN 623-2
Water Absorption	0.00 %	0.00 %	Open Porosity; DIN EN 623-2
Permeability	0.00	0.00	%, Gas
Weibull Modulus	10	10	DINV ENV 843-5

Mechanical Properties	Metric	English	Comments
Vickers Microhardness	1750	1750	HV1; DINV ENV 843-4
Tensile Modulus	390 GPa	56600 ksi	Young's; DINV ENV 843-2
Flexural Strength	300 MPa	43500 psi	DIN EN 843-1
Compressive Strength	2500 MPa	363000 psi	DIN 51067T1
Poissons Ratio	0.23	0.23	DINV ENV 843-2
Fracture Toughness	5.40 MPa-m ^{1/2}	4.91 ksi-in ^{1/2}	K _{IC} (SEVNB); DIN CEN/TS 14425-1
Shear Modulus	159 GPa	23100 ksi	Calculated

Thermal Properties	Metric	English	Comments
CTE, linear	7.50 µm/m-°C	4.17 µin/in-°F	DIN EN 821-1
	@Temperature 20.0 - 400 °C	@Temperature 68.0 - 752 °F	
	8.50 µm/m-°C	4.72 µin/in-°F	DIN EN 821-1
	@Temperature 20.0 - 1000 °C	@Temperature 68.0 - 1830 °F	
Specific Heat Capacity	0.900 J/g-°C	0.215 BTU/lb-°F	DINV ENV 821-3
Thermal Conductivity	30.0 W/m-K	208 BTU-in/hr-ft ² -°F	DIN EN 821-2
Maximum Service Temperature, Air			

Thermal Properties	1500 °C Metric	2730 °F English	Comments
Maximum Service Temperature, Inert	1500 °C	2730 °F	

Component Elements Properties	Metric	English	Comments
Al2O3	99.7 %	99.7 %	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 672-1
	@Temperature 400 °C	@Temperature 752 °F	
	1.00e+14 ohm-cm	1.00e+14 ohm-cm	IEC 672-1
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Dielectric Constant	9.0	9.0	IEC 672-1
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 672-1
Dielectric Loss Index	0.0010	0.0010	IEC 672-1
	@Frequency 9.00e+9 Hz	@Frequency 9.00e+9 Hz	

Descriptive Properties	Value	Comments
Ra = Arithmetic Mean Roughness Value (µm)	<0.1	
Thermal Shock Resistance R1 (K)	79	calculated; $R1 = [s^2 (1-\mu)] / (a \cdot E)$

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China