

Chase Plastics CP Pryme® NN300HSL (COND, 50% RH) Nylon 66 (Utility Grade), Heat Stabilized, Internally Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Heat Stabilized

Material Notes:

Information provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-NN300HSL-COND-50-RH-Nylon-66-Utility-Grade-Heat-Stabilized-Internally-Lubricated.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	56.5 MPa	8200 psi	ASTM D638
Flexural Strength	37.2 MPa	5400 psi	ASTM D790
Flexural Modulus	1.03 GPa	150 ksi	ASTM D790
Izod Impact, Notched	1.49 J/cm	2.80 ft-lb/in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China