

Chem Polymer Chemlon 233 GI Nylon 6, 33% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

Material Notes:

A 33% glass fiber reinforced, impact modified nylon 6 offering a combination of creep resistance, stiffness and toughness over unmodified nylon 6 materials. Data provided by the manufacturer, Chem Polymer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chem-Polymer-Chemlon-233-GI-Nylon-6-33-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	145 MPa	21000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Yield Strength	203 MPa	29400 psi	ASTM D790
Flexural Modulus	6.90 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	1.85 J/cm	3.47 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	215 °C	419 °F	ASTM D789

Processing Properties	Metric	English	Comments
Melt Temperature	254 °C	489 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China