

Chevron Phillips 1008.5 Injection Molding Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Molded

Material Notes:

Resin Type: Homopolymer; ASTM D 4976 Classification: PE 112, A 14200
 Characteristics: Excellent Flexibility, Excellent Flow, Good Warping
 Resistance, Moderate Mold Release, Moderate ESCR
 Applications: Large Housewares, Tamper Evident Snap-On Caps
 Data provided by
 Chevron Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-10085-Injection-Molding-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in ³	ASTM D1505
Melt Flow	21 g/10 min	21 g/10 min	ASTM D 1238
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50	50	ASTM D2240
Tensile Strength, Ultimate	11.2 MPa	1620 psi	ASTM D638
Tensile Strength, Yield	7.70 MPa	1120 psi	ASTM D638
Elongation at Break	540 %	540 %	ASTM D638
Flexural Modulus	0.124 GPa	18.0 ksi	3 pt. secant; ASTM D790
	0.159 GPa	23.1 ksi	3 pt. Tangent; ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	87.0 °C	189 °F	ASTM D1525
Brittleness Temperature	<= -72.0 °C	<= -97.6 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China