

Chevron Phillips 1400 Injection Molding Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Molded

Material Notes:

Resin Type: Homopolymer; ASTM D 4976 Classification: PE 113, A 24200 Characteristics: Good Flexibility, Good Flow, Good Warping Resistance, Good Mold Release, Good ESCR Applications: Lids & Closures, Caulk Tube Spouts Data provided by Chevron Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-1400-Injection-Molding-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.924 g/cc	0.0334 lb/in ³	ASTM D1505
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 190 °C	8.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	55	55	ASTM D2240
Tensile Strength, Ultimate	11.4 MPa	1650 psi	ASTM D638
Tensile Strength, Yield	10.8 MPa	1570 psi	ASTM D638
Elongation at Break	500 %	500 %	ASTM D638
Flexural Modulus	0.186 GPa	27.0 ksi	3 pt. secant; ASTM D790
	0.255 GPa	37.0 ksi	3 pt. Tangent; ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	99.0 °C	210 °F	ASTM D1525
Brittleness Temperature	<= -72.0 °C	<= -97.6 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China